



HDPE EX5

High density Polyethylene

*Test specimen from compression moulded sheet at 23°C.

*FRR values are statistical and calculated by dividing MFR values.

*Noth Impact Test specimen from compressed moulded sheet 23°C and The data quoted are average \leq values.

Producer:

Jam Petrochemical Company

No	Property	Value	Units	Test Method
1	Density	0.949	g/cm3	ISO 1183
2	FISH Eye Note	≤ 3	note	Internal
3	FRR 21.6/5	29	-	-
4	MFR 190°C/21.6	8.0	g/10min	ISO 1133
5	MFR 190°C/5	0.28	g/10min	ISO 1133

Applications:

- Blow
- Film

